



C056 Air-Dry Clear

HYFLASH


Description:

Hyflash C056 is a conventional scratch resistant Air-Dry Clearcoat with premium finishing properties. It is recommended for high performance bodyshops focusing on efficiency, space utilization and cost reduction with no compromise on premium quality. It can be simply flattened and polished after 1 hour at application temperature.

It uses the same HS hardener family (H050, H060, H070) as other premium clearcoats in the HYMAX range, providing a complete and compact offer.

Suitable Substrates:


- HyFlow Basecoat.
- HyDrobase Basecoat



Mix 2:1:10-15% with H050, H060, H070 Hymax Hardener and Thinner

100%	50%	10-15%
C056	H050 FAST HS HARDENER	S11 THINNER
C056	H060 NORMAL HS HARDENER	S11 THINNER*
C056	H070 SLOW HS HARDENER	S21 THINNER

**Recommended*



17-19 s / DIN 4 mm / 20°C
Potlife: 60 minutes at 20°C



HVLP 1.2 – 1.3 mm



1 medium + 1 full coat
3-5 minutes between coats
35 – 45 micron
2.0 – 2.2 bar inlet pressure



Dust free after	15 minutes @ 25 °C (77°F) 25 minutes @ 20 °C (68°F)
-----------------	--

Touch free after	20 minutes @ 25 °C (77°F) 45 minutes @ 20 °C (68°F)
------------------	--

Sandable & Polishable after	60 minutes @ 25 °C (77°F) 90 minutes @ 20 °C (68°F)
-----------------------------	--

Important note : below 15°C
Do not air-dry
Low bake 5-10 minutes @ 60°C panel temperature

Product Data Sheet



C056 Air-Dry Clear

HYFLASH



5 Minutes at 60°C (140 °F) Panel Temperature.



5-7 minutes, depending on color.
Substrate temperature 80°C-100°C (176°F to 212°F)
**Important note: keep panel at greater than 80cm from IR unit, depending on repair film thickness.*



Wear suitable protection

**VOC
(2004/42/EC):**

VOC (2004/42/EC): 2004/42/EC IIB (e) (840)465. The EU limit value for this product (product category IIB. e) in ready to use form is max 840g/ltr. The VOC content of this product in ready for use form is max. 465 g/l.

Specific Gravity: 0.994 kg/cm³

Flash Point: 25°C (77°F)

Solids Content: Approximately 48 % by weight RFU

Coverage: 7-8 m²/l at 35-45 micron film thickness (theoretical)

SDS: Refer to the safety data sheet

Product Data Sheet