

Description:

Hydrobase[™] is a premium, high quality Waterborne Automotive Basecoat, which offers outstanding one coat coverage, leading to a high efficiency, and ease of use and complies with all applicable VOC regulations when properly clear coated.

Suitable Substrates:

- Original or old Paint that has through hardened.
- 2K Rapid Primer P42

Surface Preparation:

- Degrease S22 degreaser
- Wipe dry completely before applying color.
- Use only special "Base Coat Tack Rags" that leave no sticky trace behind.



Clean panels prior to painting with S22 degreaser Wipe dry completely before applying colour

Mixing ratio is 1 part Hydrobase[™] Basecoat to 10% - 20% WS20 Demineralized water Optimum viscosity 22 to 24 sec/DIN4mm/ 20[°]C

HVLP 1.2 – 1.3 2.0 – 2.5 bar inlet pressure 1.5 = 15-25 micron



<u>}</u>

1

1 Full wet coat. Dry before applying mist coat. Apply Mist Coat

Final flash off until matt





Can be overcoated with all Hymax Clear Coats

Flash off time can be reduced by:

- Using air blower after a 5 minute flash off.
- Spray booth blower system
- Infrared drying
- Increasing spray booth temperature



Wear suitable protection

Specific Gravity: 1.01 – 1.19 grams/liter

Solids Content: 16.18% – 39.83% by weight

VOC (2004/42/EC): 2004/42/IIB (c) (420)420. The EU limit value for this product (product category IIB.c) in ready to use form is max 420g/ltr. The VOC content of this product in ready for use form is max. 420 g/l.

SDS:

See the safety data sheet