



B995- MetalliteAluminium

Description:

B995 Metallite Aluminum is a basecoat mixing toner used to achieve a chrome-like effect mostly for OEM wheel silvers and some new OEM bright metallic colors.

B995 must be recoated with a “Hymax” clearcoat. When used as a standalone product to achieve the brightest aluminum color, please follow the TDS below. When used as a toner within a basecoat formula, please adhere to the TDS of the Hymax B Series.


Suitable Substrates:

- Substrates which have just been coated with Mix T830 Hymax 2K.


Surface Preparation

Apply Metallite Aluminium over freshly baked and sanded Mix T830 Hymax 2K. Please follow the directions for application and baking of the undercoat as indicated in the Hymax 2K (T series) TDS sheet.

Lightly sand the undercoat, after cooling down, using a P2000 or P3000 trizact sanding pad.



Mix 125% with Hymax Reducer.




Spraying Viscosity. 14s DIN Cup 4 at 20 C



Compliant 1.3 – 1.4 mm
2.0 – 2.5 bar inlet pressure
HVLP 1.3 - 1.4 mm;0.7 bar at the air-cap



Three to four thin single coats



5-10 minutes between coats at 20°C (68°F)
20 minutes at 20°C (68°F) before applying clearcoat.



B995- Metallite Aluminium



Wear suitable protection

Flash Point: 24° C

Solids Content: 23.7%

VOC: 727 grams/liter

SDS: See the safety data sheet