

Description:

P08 is a 1K tintable automotive sealer with a velvet smooth finish, P08 is part of the Hymax mixing system making it totally compatible with the Hymax basecoat tints. P08 has no sensitive recoat issues. P08 dries quickly, helps hold down sand scratches, and provides color uniformity for the basecoat color.

Surface Preparation:

Old paint well sanded and surfaces well primed and prepared.

Suitable Substrates:

- Existing Finishes except TPA
- "HYMAX" 1 K or 2 K primers
- o OEM Primer or EDP, sanded
- "HYMAX" Polyester Putties
- Bare metal substrates must be pre-primed with wash primer P97



100% "Hymax" thinners (as a clear sealer)

Mix one (1) part P08 Sealer with one (1) to (2) parts B Series Tints (depending on color opacity). Reduce 75% with appropriate speed Hymax Reducer.

Mix one (1) part P08 to one (1) part Hymax Reducer to use as a clear sealer.



18-19 sec / DIN 4 mm / 20 °C (68 °F)



Compliant 1.4–1.5 mm 2.0–2.5 bar inlet pressure HVLP 1.4–1.5 mim; 0.7 bars at the air-cap 8-12 microns per coat



1

5 min. between coats.



$\frac{1}{2}$	Wait until fully matt before applying top coat.
Flash Point:	27°C
Specific Gravity:	1.09 kg/cm ³
Solids Content:	42 % by weight
Coverage:	$8 - 10 \text{ m}^2/\text{l}$ at 25 micron dry thickness
SDS:	See the safety data sheet