

P424/6 2K VOC Primer

HYFLASH

Description:

HyFlash P424 and P426 is a VOC High Build Air-Dry 2K Primer with excellent filling properties and sandability. It is recommended for high performance bodyshops focusing on efficiency, space utilization and cost reduction with no compromise on premium quality. (Available in Grey - P420 White- P424 and Dark grey - P426)

HyFlash P424 and P426 is easy to sand within 1 hour from application. It maintains an excellent gloss holdout when topcoated with any Hymax topcoating material.

It uses the same HS hardener family (H050, H060) as other primers in the Hymax range, providing a complete and compact offer

Suitable Substrates:

- Old and Sound thermoset topcoats.
- Hymax polyester fillers.
- Sound OEM



Mix 100 :	25 : 5-25% with H	1050, H060 General Hardener and Thinner
100%	25%	525%
P424/6	H050 FAST H	IS HARDENER S19 THINNER*
P424/6	H060 NORM	AL HS HARDENER S11 THINNER

*Recommended

18-19 s / DIN 4 mm / 20°C Potlife: 40 minutes at 20°C



HVLP 1.6 - 1.8 mm



3-5 minutes between coats
2-3 coats
45-50 microns/coat
2.0 - 2.2 bar inlet pressure

THINNING RATIO%	VISCOSITY	FILM THICK- NESS/COAT	3 COATS TOTAL FILM BUILD
5%	40"	70 μ	210µ
10%	30"	67 μ	200μ
15%	25"	65 μ	195µ
20%	22"	60 µ	180µ
25%	19"	55 μ	165µ



P424/6 2K VOC Primer

HYFLASH

	Dust free after10 minutes @ 20 °C (68°F)Touch free after15 minutes @ 20 °C (68°F)Sandable after60 minutes @ 20 °C (68°F)Depending on the film thickness60 minutes @ 20 °C (68°F)Important note :below 15°CDo not air-dryLow bake 5-10 minutes @ 60°C panel temperature	et
LOW BAKE	5 Minutes at 60°C (140 °F) Panel Temperature.	bhe
	 5-7 minutes, depending on color. Substrate temperature 80°C-100°C (176°F to 212°F) *Important note: keep panel at greater than 80cm from IR unit,depending on repair film thickness. 	ta
	Wear suitable protection	Da
VOC (2004/42/EC):	VOC (2004/42/EC):2004/42/EC IIB (c) (540)540. The EU limit value for this prod- uct (product category IIB. c) in ready to use form is max 540g/ltr. The VOC content of this product in ready for use form is max.540 g/l.	JCt
Specific Gravity:	P420 (Grey) = 1.64 kg/cm ³ P424 (White)= 1.637 kg/cm ³ P426 (Dark Grey)= 1.493 kg/cm ³	1po
Flash Point:	25°C (77°F)	Pr
Solids Content:	Approx. 62.5% - 67.5% by weight RFU, depending on reduction ratio	
Coverage:	5.7-5.8 m ² /l at 80 micron film thickness (theoretical)	
SDS:	Refer to the safety data sheet	

General Paint Co. P.O.Box: 7623 Beirut - Lebanon - Tel: 09 925991/2 - Fax: 09 925993 - e-mail: info@hymax.biz