

## **Description:**

C090 2K Plasticizer Matt is a universal plasticizer for all MS and VOC topcoat systems. It is suitable for Hymax filler and plastic finishes. C090 demonstrate high long-term elasticity.

Preparation:	<ul> <li>Can be used for all car plastic panels.</li> <li>Add 15% of plasticizer to topcoats, clearcoats and fillers with medium and hard plastics.</li> <li>Add 50% of plasticizer to topcoats, clearcoats and fillers with soft plastics.</li> </ul>	
	Addition of C090 to T830 clear	Gloss level at 60 degrees
	50%	75-85%
	100%	65-75%
	150%	50-60%
	200%	10-20%
Flash Point:	27° C /80.6° F	
Solids Content:	46.8 Weight %	
Specific Gravity:	1.032 g/cm <sup>3</sup>	
Cleaning the Equipment:	Clean after use with Hymax cleaning thinner.	
Important Remarks:	<ul> <li>Hymax 2K Plasticizer Matt must be included before the addition of 2K hardener.</li> <li>To optimize the sanding properties the plasticized fillers should be dried 45 min/60-65 ° C panel temperatures. C090 may be added in a maximum proportion of 1:1 for maximum plasticizing effect.</li> <li>When C090 is added to Hymax 2K systems, it slows down the drying.</li> </ul>	
Safety:	Refer to Material Safety Data Sheet (MSDS) for complete safety instructions. The technical data sheet listed has been compiled in good faith for your con- venience and guidance. No warranty, expressed or implied, is intended or given by the information on this sheet.	
	Note: Hymax recommends that our products not be used under 10°C. Usage below 10°C can result in extended drying times or product failure.	