




## C020 - 2K HS Clear North American Market Only

### Description:

This 2.1 VOC compliant 2 coats clear coat system has an excellent adhesion on waterborne or solvent basecoats and is very easy to apply. It is extremely stable when applied on vertical surfaces and it can be overcoated within 24h without intermediate sanding.

### Suitable Substrates:

- Hymax basecoat
- Hydrobase basecoat



Mix 2:1 with any of the following hardeners:

- HU08 slow
- HU07 normal
- HU05 fast

Potlife: 5h at 20°C (68°F)



16-18s / DIN 4 mm / 20°C (68°F)



Compliant 1.3 – 1.5 mm (2 spray passes)  
2.0 - 2.5 bar inlet pressure (29 – 36.25 PSI)  
2 = 50 – 60 micron



HVLP 1.3 – 1.5 mm ( 2 spray passes)  
0.7 bar atomization pressure (29 – 36.25 PSI)  
2 = 50 – 60 micron



Wait 10 min before increasing temperature  
Bake 20 min at 60°C panel temperature



## C020 - 2K HS Clear

### North American Market Only



Short Wave 8 min.  
The object should be maintained at greater than 60cm from source.



Wear suitable protection

---

**Flash Point:** 25°C (77°F)

---

**Solids Content:** 42.6 % by weight

---

**Specific Gravity:** 1.05kg/cm<sup>3</sup> (8.74 lbs/gal)

---

**Coverage:** 8 - 9 m<sup>2</sup>/l at 50 micron dry film thickness (theoretical)

---

**SDS:** See the safety data sheet