



C076 Air-Dry VOC Clear

HYFLASH

North American Market Only


Description:

Hyflash C076 is a VOC compliant Air-Dry Clearcoat with premium finishing properties. It is recommended for high performance bodyshops focusing on efficiency, space utilization and cost reduction with no compromise on premium quality. It can be simply flattened and polished after 1 hour at application temperature.

It uses the existing L.E Hardeners (H082, H092) as other VOC clearcoats in the HYMAX range, providing a complete and compact offer.


Suitable Substrates:

- HyFlow Basecoat.
- HyDrobase Basecoat
- HyVida Basecoat



Mix 2:1 with H082, H092 Hymax Hardeners

100%	50%
C076	H082 FAST UHS HARDENER
C076	H092 SLOW UHS HARDENER



17-19 s / DIN 4 mm / 20°C (68°F)
Potlife: 60 minutes at 20°C (68°F)



HVLP 1.2 – 1.3 mm



1 light + 1 full coat
No flash-off between coats
35 – 45 micron
2.0 – 2.2 bar inlet pressure



Dust free after	15 minutes @ 25 °C (77°F)
	30 minutes @ 20 °C (68°F)

Touch free after	20 minutes @ 25 °C (77°F)
	45 minutes @ 20 °C (68°F)

Sandable & Polishable after	60 minutes @ 25 °C (77°F)
	90 minutes @ 20 °C (68°F)

Product Data Sheet



C076 Air-Dry VOC Clear

HYFLASH
North American Market Only



5 Minutes at 60°C (140 °F) Panel Temperature.



5-7 minutes, depending on color.
Substrate temperature 80°C-100°C (176°F to 212°F)
***Important note: keep panel at greater than 80cm from IR unit, depending on repair film thickness.**



Wear suitable protection

Specific Gravity: 0.997 kg/cm³ (8.31997 lbs/gal)

Flash Point: 25°C (77°F)

Solids Content: Approximately 56 % by weight RFU

Coverage: 7-8 m²/l at 35-45 micron film thickness (theoretical)

SDS: Refer to the safety data sheet

Product Data Sheet