



C090 2K Plasticizer Matt

Description:

C090 2K Plasticizer Matt is a universal plasticizer for all MS and VOC topcoat systems. It is suitable for Hymax filler and plastic finishes. C090 demonstrate high long-term elasticity.

Preparation:

- Can be used for all car plastic panels.
- Add 15% of plasticizer to topcoats, clearcoats and fillers with medium and hard plastics.
- Add 30% of plasticizer to topcoats, clearcoats and fillers with soft plastics.

addition of C090 to T830 clear	Gloss level at 60 degrees
50%	75-85%
100%	65-75%
150%	50-60%
200%	10-20%

Flash Point: 27° C /80.6° F

Specific Gravity: 1.032 g/cm³

Solids Content: 46.8 Weight %

Cleaning the Equipment: Clean after use with Hymax cleaning thinner.

IMPORTANT REMARKS:

- Hymax 2K Plasticizer Matt must be included before the addition of 2K hardener.
 - To optimize the sanding properties the plasticized fillers should be dried 45 min/60-65 ° C panel temperatures. C090 may be added in a maximum proportion of 1:1 for maximum plasticizing effect.
 - When C090 is added to Hymax 2K systems, it slows down the drying.
-

SAFETY:

Refer to Material Safety Data Sheet (MSDS) for complete safety instructions. The technical data sheet listed has been compiled in good faith for your convenience and guidance. No warranty, expressed or implied, is intended or given by the information on this sheet.

Note: Hymax recommends that our products not be used under 10°C. Usage below 10°C can result in extended drying times or product failure.
